

Product Specification Sheet

Calcium Lignosulphonate

No. SMRP023-0

Other Names	Calcium Lignosulfonate		
Items/Grades	CL-65	CL-60	CL-50
Appearance	Pale Brown Powder	Yellow Powder	Yellow Powder
Lignosulphonate Content (%)	≥65	≥60	≥50
Sugar Content (%)	3-5	6-9	8-10
Calcium Content (%)	10-12	5-7	4-6
Dry Matter (%)	≥95	≥95	≥94
Ash (%)	≤13	≤13	≤14
Water Insoluble (%)	≤0.5	≤0.5	≤1
Moisture (%)	≤5	≤5	≤5
PH Value (10% Aqueous Solution)	6.5-7.8	4-7	4-6
Fineness (0.18~0.125mm, %)	95min	95min	95min
Packing	25kg in one paper bag and 500-700 kg on one pallet, 10-14 metric tons/20'FCL.		
Ligno Resource	Pine Pulp	Poplar Pulp	Wheat Straw Pulp

Neomatek

Luoyang Neomatek Co., Ltd

1203, Guobao Building, 261 Kaiyuan Avenue, Luoyang 471026, China

Tel: +86-379-6333-8198 Fax: +86-379-6333-8197 Email: neomatek@neomatek.com