

**Sodium Silicate Powder**

No. SMRP019-0

Other Names		Hydrous Powder Sodium Silicate, Instant Sodium Silicate			
Items/Grades		SSP-215	SSP-250	SSP-325	NSSP-320
Chemical Compositions (%)	Mol Ratio	2.05-2.25	2.35-2.65	3.15-3.35	3.0-3.4
	SiO <sub>2</sub>	50-58	50-60	56-64	71-77
	Na <sub>2</sub> O	22-28	20-26	17-23	21-27
	Al <sub>2</sub> O <sub>3</sub>	---	---	---	<=0.5
	Fe <sub>2</sub> O <sub>3</sub>	---	---	---	<=0.05
	TiO <sub>2</sub>	---	---	---	<=0.05
	K <sub>2</sub> O	---	---	---	<=0.02
Physical Properties	Moisture (%)	13-20	13-20	13-20	<=0.3
	Bulk Density (g/cm <sup>3</sup> )	0.5-0.8	0.5-0.8	0.5-0.8	0.95-1.25
	Whiteness (%)	>=80	>=80	>=80	>=70
Fineness (%)		-0.125mm(100mesh), 90min			-200mesh, 80min
Packing		20-25kg in one paper bag, 800-1000kg in one jumbo bag, 16MT in 1x20'fcl			20-25kg in one paper bag, 1000kg in one jumbo bag, 20MT in 1x20'fcl

**Neomatek****Luoyang Neomatek Co., Ltd**

1203, Guobao Building, 261 Kaiyuan Avenue, Luoyang 471026, China

Tel: +86-379-6333-8198 Fax: +86-379-6333-8197 Email: neomatek@neomatek.com